



Química Interprima, C.A.

RIF J-31670947-7

TECHNICAL DATA SHEET

HANGZHOU HONGYAN PIGMENT CHEMICAL CO.LTD

ADD: Room A-903, International Business Center, Jincheng Rd. 466, Xiaoshan Hangzhou China 311202

Tel: 0086-571-5617 7009 Fax: 0086-571-8289 0877 www.hy-pigment.com nancy@hy-pigment.com

Ultramarine Blue	
Heat Resistance °C ≤	300°C
PH Value	7.5-8.0
Oil Absorption	25-35
Volatile(105±2°C) ≤ %	1.50
dissociate sulfur ≤ %	0.05
Residues On Sieve	0.10
Soluble matter in water %	0.50
lead content ≤%	30 ppm
Color index	PB29