

HANGZHOU HONGYAN PIGMENT CHEMICAL CO.LTD

ADD: Room A-903, International Business Center, Jincheng Rd. 466, Xiaoshan Hangzhou China 311202

Tel: 0086-571-5617 7009 Fax: 0086-571-8289 0877.

Technical Data Sheet

Pigment Red 122	
Density(g/cm3)	1.45
Bulk Density (ml/kg)	6
Specific surface area(m2/g)	62
Average partical(nm)	350
PH Value	5-8
Oil absorption(ml/100gr)	60
Shade(Against standard)	Similar
Strength(Against standard)	95-105
Viscosity mm2/s	10-15
Matter Volatile at 105℃	0.65%
Matter Soluble in Water	0.35%
Residus On sieve(60 Mesh)	≤1. 0%
Chromatic Aberration	0.953
Solvent Mixture	5
Ethanol	5
Ethyl Acetate	5
MEK	4-5

Toluene	4-5
White Sprit	5
DBP	5
Paraffine	5
Butter	5
Soap	5
Alkali	5
Acid	5
Heat resistance	300
Light fastness	7-8