



EPOXY CURING AGENT

Phenolic Amine T-31

Description

T-31, modified fatty amine curing agent, generated by phenol, formaldehyde and multiple amine. It has high bonding strength, high hardness, low curing shrinkage rate, can be cured at low temperature, room temperature, humidity and underwater.

It is widely used in civil engineering and the composition of epoxy resin adhesive, also used in the dark paint, anti-corrosion materials and other industries.

Typical properties

Appearance	Brownish yellow transparent liquid
Amine value mgKOH/g	480 ± 20
Viscosity mPa.s/40 °C	200-500
Color (Fe-Co)	-

Storage

T-31 should be stored in dry, cool, ventilated warehouse, away from the fire. Room temperature should be controlled below 35 °C. Warehouse lighting and Electrical appliances should be explosion-proof type.

Handling

Please refer to MSDS for safe handling of T-31 .



Chemical World MGUS, LLC

Disclaimer

All recommendations for use of our products whether given by us in writing, verbally or to be implied from the results of tests carried out by us are based on the current state of our knowledge. Although, the information contained in this sheet is accurate, no liability can be accepted in respect of such information. We warrant only that our product will meet the designated specifications and make no other warranty either express or implied, including any warranty of merchantability or fitness for a particular purpose as the conditions of application are beyond our control.

